



Cleaner Blend Aqua100

Description:	DEVCON Cleaner Blend Aqua100 is a water-based corrosion preventive surface treatment solution for metals. This solution delivers temporary protection (24-48 hours) against flash rust on most of the metal surfaces including aluminium, zinc, zinc alloy, mild steel, cold rolled steel and blasted metal surfaces. It is a no-rinse treatment for spray and wipe applications. It is compatible with most coatings as well as most paints.										
Intended Use:	<p>Cleaning of the following surfaces before coating application.</p> <ul style="list-style-type: none">▪ Rusted steel surfaces▪ Ferrous components▪ Gutters & roofs▪ Concrete reinforcing bars										
Typical Physical Properties:	<p>Technical data should be considered representative or typical only and should not be used for specification purposes.</p> <table><tr><th>Property</th><th>Typical values</th></tr><tr><td>Appearance</td><td>Colourless liquid</td></tr><tr><td>Density</td><td>1.01 g/cm³</td></tr><tr><td>pH</td><td><1</td></tr><tr><td>Flash point</td><td>No flash point up to 100°C (aqueous preparation)</td></tr></table>	Property	Typical values	Appearance	Colourless liquid	Density	1.01 g/cm ³	pH	<1	Flash point	No flash point up to 100°C (aqueous preparation)
Property	Typical values										
Appearance	Colourless liquid										
Density	1.01 g/cm ³										
pH	<1										
Flash point	No flash point up to 100°C (aqueous preparation)										
Directions for use:	<ul style="list-style-type: none">▪ Remove loose rust and scale with a wire brush to achieve a firm rusted surface.▪ Apply DEVCON Cleaner Blend Aqua100 on a clean surface by spraying or wiping methods, at a temperature between 20 to 40 °C.▪ Wipe off excess if necessary, leaving a thin film and allow parts to dry▪ CAUTION: DEVCON Cleaner Blend Aqua100 contains complex fluorides in the formulation. Refer SDS for safe handling of this material.▪ Recommended to apply surface coatings after complete drying of the surface.										
Storage:	Store this product in an unopened container in a dry location. Keep containers tightly closed in a dry, cool and well-ventilated place. Keep in properly labelled containers. Long term storage below 8 °C or greater than 30 °C can adversely affect product properties.										
Warranty:	ITW India Private Limited will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.										
Order Information:	Please check with ITW India Private Limited on the available pack sizes										
Contacts:	<p>ITW India Limited Plot No: 34 to 37, Phase-2, IDA, TSIIC, IDA, Pashamylaram, Hyderabad, Telangana 502307</p> <p>TEL: +91-9000031515 Email : chemininfo@itwchemin.com</p>										
Disclaimer:	<p>Product Use: The information herein is based upon good faith testing that ITW India believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW India control and uniquely within user's knowledge and control can affect the use and performance of an ITW India product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsible for evaluating any ITW India product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.</p> <p>Exclusion of Warranties: As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW India makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW India shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability</p>										