



Corrosion Primer CP-10

Description:

DEVCON Corrosion Primer CP-10 is a fast-reacting rust neutralizer and sealer which can be applied directly to a rusty surface. DEVCON Corrosion Primer CP-10 reacts with rust to form a black chelate compound which binds to the surface.

DEVCON Corrosion Primer CP-10 is used where it is impossible or impractical to remove rust before painting.

Clean up and use of DEVCON Corrosion Primer CP-10 is easy because it is water based. DEVCON Corrosion Primer CP-10 does not need to be rinsed off the surface before top-coating like other similar products on the market.

To full protect the metal substrate apply Primer and Topcoat materials within 3 months of surface preparation with DEVCON Corrosion Primer CP-10.

Intended Use:

- Rusted steel surfaces
- Ferrous components
- Gutters & roofs
- Concrete reinforcing bars

Features:

Easy to use.
May be applied to a damp surface.
Enamel paint can be applied after 3 hours.
No residue to wash off.
Provides a tough and flexible film.
Contains no phosphoric acid.

Typical Physical Properties:

Technical data should be considered representative or typical only and should not be used for specification purposes.

Property	Typical Values
Classification	Rust neutralizer / sealer
Binder Type	Acrylic vinyl copolymer
Colour	Off White
Active Pigment	Tannic acid
Touch Dry	30 minutes
Recoat after	3 hours
Temperature Range	up to 100°C Recommended
Dry Film Thickness	50 – 75 microns
Coverage per coat	8 m ² per litre
Thinner (clean-up)	Water

Surface Preparation:

- Proper surface preparation is essential for obtaining maximum performance from this product.
- Remove loose rust and scale with a wire brush to achieve a firm rusted surface.
- Rinse with water or solvent to remove loose dust particles.
- Brush DEVCON Corrosion Primer CP-10 onto the rusty surface. It may be applied to damp, but not wet surfaces.

Mixing Instructions:

- Before use, gently invert bottle several times to ensure homogenous mixture. Do not shake vigorously.
- Pour DEVCON Corrosion Primer CP-10 into a plastic or non-ferrous container.

Application Instructions:

- Brush DEVCON Corrosion Primer CP-10 onto the rusty surface. It may be applied to damp, but not wet surfaces.
- DEVCON Corrosion Primer CP-10 may be top-coated with enamel paints after 3 hours, or two-pack paints after 24 hours.

Clean Up:

Water (or) Recommended DEVCON Cleaner Blend Aqua100 water-based cleaner for high efficiency.

Storage:

Store at room temperature in dry conditions away from sources of heat and naked flames. Protect from frost. When stored in original sealed containers, the minimum shelf life is 2 years.

Precautions:

Only for use on rusted steel surfaces.

Warranty:

ITW India Private Limited will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

**Order
Information:**

Please check with ITW India Private Limited on the available pack sizes

Contacts:

ITW India Limited
Plot No: 34 to 37, Phase-2, IDA,
TSIIC, IDA, Pashamylaram,
Hyderabad, Telangana 502307

TEL: +91-9000031515
Email: chemininfo@itwchemin.com

Disclaimer:

Product Use: The information herein is based upon good faith testing that ITW India believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW India control and uniquely within user's knowledge and control can affect the use and performance of an ITW India product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsible for evaluating any ITW India product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.

Exclusion of Warranties: As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW India makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW India shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability